



16015 Shady Falls Road
Elmendorf, TX 78112
Phone: (210) 635-8100
Fax: (210) 635-8101

NFPA 701 DRAFT RESULTS SHEET

TO: John Snook, Thermotex Industries
DATE: May 10, 2016
PROJECT NO.: 102506902SAT-006

TEST CRITERIA

No specimen shall continue flaming for more than two seconds. Length of char shall not exceed 17.1 inches from the bottom edge of the specimen. No flaming on floor of apparatus is allowed for longer than two seconds.

Specimen #	Afterflame Duration (sec.)	Floor Flaming (sec.)	Char Length (in.)
1	0	0	6
2	0	0	6
3	0	0	5
4	0	0	6.5
5	0	0	6
6	0	0	5.5
7	0	0	6
8	0	0	5.5
9	0	0	6
10	0	0	5
Average	0	0	5.8

The sample **Fiberglass Curtain - Beige MET** the requirements of the NFPA 701 Test Method 2.

If this transmission was incomplete, please notify by telephone at (210) 635-8100.

"The information in this document is confidential and is being transmitted to and is intended only for the use of the individual or entity named above. If the reader of this message is not the intended recipient, please be advised that any dissemination, distribution or copying of this transmission is strictly prohibited. If you received this document in error, please advise us immediately by telephone and destroy this document."